



US008486436B2

(12) **United States Patent**
Boyan et al.

(10) **Patent No.:** **US 8,486,436 B2**
(45) **Date of Patent:** ***Jul. 16, 2013**

(54) **ARTICULAR JOINT IMPLANT**

(75) Inventors: **Barbara D. Boyan**, Atlanta, GA (US);
Stephen J. Kennedy, Alpharetta, GA
(US); **Zvi Schwartz**, Atlanta, GA (US)

(73) Assignee: **Georgia Tech Research Corporation**,
Atlanta, GA (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

This patent is subject to a terminal dis-
claimer.

(21) Appl. No.: **13/427,648**

(22) Filed: **Mar. 22, 2012**

(65) **Prior Publication Data**

US 2012/0185051 A1 Jul. 19, 2012

Related U.S. Application Data

(63) Continuation of application No. 12/117,673, filed on
May 8, 2008, now Pat. No. 8,142,808, which is a
continuation of application No. 11/053,410, filed on
Feb. 7, 2005, now Pat. No. 8,002,830.

(60) Provisional application No. 60/542,514, filed on Feb.
6, 2004.

(51) **Int. Cl.**
A61F 2/30 (2006.01)

(52) **U.S. Cl.**
USPC **424/423**; 623/18.11; 623/23.5; 623/23.76

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,276,996 A 10/1966 Lazare
3,663,470 A 5/1972 Nishimura et al.
3,673,612 A 7/1972 Merrill et al.
3,849,238 A 11/1974 Gould et al.
3,859,421 A 1/1975 Huckle
4,083,906 A 4/1978 Schindler et al.
4,205,400 A 6/1980 Shen et al.
4,351,069 A 9/1982 Ballintyn et al.
4,472,542 A 9/1984 Nambu
4,517,295 A 5/1985 Bracke et al.
4,524,064 A 6/1985 Nambu
4,609,337 A 9/1986 Wichterle et al.
4,663,358 A 5/1987 Hyon et al.
4,664,857 A 5/1987 Nambu
4,693,939 A 9/1987 Ofstead
4,731,081 A 3/1988 Tiffany et al.
4,734,097 A 3/1988 Tanabe et al.
4,738,255 A 4/1988 Goble et al.
4,753,761 A 6/1988 Suzuki
4,759,766 A 7/1988 Buettner-Janz et al.
4,772,284 A 9/1988 Jefferies et al.
4,784,990 A 11/1988 Nimrod et al.
4,787,905 A 11/1988 Loi
4,808,353 A 2/1989 Nambu et al.
4,828,493 A 5/1989 Nambu et al.

4,851,168 A 7/1989 Graiver et al.
4,911,720 A 3/1990 Collier
4,916,170 A 4/1990 Nambu
4,988,761 A 1/1991 Ikada et al.
4,995,882 A 2/1991 Destouet et al.
5,047,055 A 9/1991 Bao et al.
5,080,674 A 1/1992 Jacobs et al.
5,095,037 A 3/1992 Iwamitsu et al.
5,106,743 A 4/1992 Franzblau et al.
5,106,876 A 4/1992 Kawamura
5,108,428 A 4/1992 Capecchi et al.
5,108,436 A 4/1992 Chu et al.
5,118,667 A 6/1992 Adams et al.
5,141,973 A 8/1992 Kobayashi et al.
5,171,322 A 12/1992 Kenny
5,171,574 A 12/1992 Kuberasampath et al.
5,192,326 A 3/1993 Bao et al.
5,206,023 A 4/1993 Hunziker
5,219,360 A 6/1993 Georgiade
5,234,456 A 8/1993 Silvestrini
5,244,799 A 9/1993 Anderson
5,258,023 A 11/1993 Reger
5,258,042 A 11/1993 Mehta
5,258,043 A 11/1993 Stone
5,260,066 A 11/1993 Wood et al.
5,287,857 A 2/1994 Mann
5,288,503 A 2/1994 Wood et al.

(Continued)

FOREIGN PATENT DOCUMENTS

DE 20218703 U1 3/2003
EP 0222404 A1 5/1987

(Continued)

OTHER PUBLICATIONS

Andrade et al., "Water as a Biomaterial," Trans. Am. Soc. Artif.
Intern. Organs, 19:1 (1973).

Ariga et al., "Immobilization of Microorganisms with PVA Hardened
by Iterative Freezing and Thawing," Journal of Fermentation Tech-
nology, 65(6): pp. 651-658 (1987).

Boyan et al., "Effect of Titanium Surface Characteristics on
Chondrocytes and Osteoblasts in Vitro," Cells and Materials, vol. 5,
No. 4, pp. 323-335 (1995).

Boyan et al., "Osteoblast-Mediated Mineral Deposition in Culture is
Dependent on Surface Microtopography," Calcif. Tissue Int., 71:519-
529 (2002).

Bray et al., Poly(vinyl alcohol) Hydrogels for Synthetic Articular
Cartilage Material, M. Biomed. Mater. Res., vol. 7, pp. 431-443,
1973.

Brunette, "The Effects of Implant Surface Topography on the Behav-
ior of Cells," Int. J. Oral Maxillofac Implants, 3:231-240 (1988).

(Continued)

Primary Examiner — Savitha Rao

Assistant Examiner — Gregg Polansky

(74) *Attorney, Agent, or Firm* — Knobbe, Martens, Olson &
Bear, LLP

(57) **ABSTRACT**

Implantable biomaterials, particularly hydrogel substrates
with porous surfaces, and methods for enhancing the com-
patibility of biomaterials with living tissue, and for causing
physical attachment between biomaterials and living tissues
are provided. Also provided are implants suitable for load-
bearing surfaces in hard tissue repair, replacement, or aug-
mentation, and to methods of their use. One embodiment of
the invention relates to an implantable spinal disc prosthesis.

20 Claims, 4 Drawing Sheets

| U.S. PATENT DOCUMENTS | | | | | | | |
|-----------------------|----|---------|---------------------|-----------|----|---------|----------------------|
| 5,290,494 | A | 3/1994 | Coombes et al. | 6,187,329 | B1 | 2/2001 | Agrawal et al. |
| 5,314,477 | A | 5/1994 | Marnay | 6,206,927 | B1 | 3/2001 | Fell |
| 5,314,478 | A | 5/1994 | Oka et al. | 6,224,630 | B1 | 5/2001 | Bao et al. |
| 5,326,364 | A | 7/1994 | Clift, Jr. et al. | 6,231,605 | B1 | 5/2001 | Ku |
| 5,336,551 | A | 8/1994 | Graiver et al. | 6,255,359 | B1 | 7/2001 | Agrawal et al. |
| 5,336,767 | A | 8/1994 | Della Valle et al. | 6,264,695 | B1 | 7/2001 | Stoy |
| 5,343,877 | A | 9/1994 | Park | 6,268,405 | B1 | 7/2001 | Yao et al. |
| 5,344,459 | A | 9/1994 | Swartz | 6,271,278 | B1 | 8/2001 | Park et al. |
| 5,346,935 | A | 9/1994 | Suzuki et al. | 6,280,475 | B1 | 8/2001 | Bao et al. |
| 5,397,572 | A | 3/1995 | Coombes et al. | 6,337,198 | B1 | 1/2002 | Levene et al. |
| 5,399,591 | A | 3/1995 | Smith et al. | 6,340,369 | B1 | 1/2002 | Ferree |
| 5,401,269 | A | 3/1995 | Buttner-Janz et al. | 6,341,952 | B2 | 1/2002 | Gaylo et al. |
| 5,409,904 | A | 4/1995 | Hecht et al. | 6,344,058 | B1 | 2/2002 | Ferree |
| 5,410,016 | A | 4/1995 | Hubbell et al. | 6,355,699 | B1 | 3/2002 | Vyakarnam et al. |
| 5,442,053 | A | 8/1995 | Della Valle et al. | 6,358,251 | B1 | 3/2002 | Mirza |
| 5,458,643 | A | 10/1995 | Oka et al. | 6,371,984 | B1 | 4/2002 | Van Dyke et al. |
| 5,458,645 | A | 10/1995 | Bertin | 6,376,573 | B1 | 4/2002 | White et al. |
| 5,486,197 | A | 1/1996 | Le et al. | 6,379,962 | B1 | 4/2002 | Holy et al. |
| 5,489,310 | A | 2/1996 | Mikhail | 6,383,519 | B1 | 5/2002 | Sapieszko et al. |
| 5,490,962 | A | 2/1996 | Cima et al. | 6,402,784 | B1 | 6/2002 | Wardlaw |
| 5,492,697 | A | 2/1996 | Boyan et al. | 6,402,785 | B1 | 6/2002 | Zdeblick et al. |
| 5,494,940 | A | 2/1996 | Unger et al. | 6,419,704 | B1 | 7/2002 | Ferree |
| 5,502,082 | A | 3/1996 | Unger et al. | 6,428,576 | B1 | 8/2002 | Haldimann |
| 5,512,475 | A | 4/1996 | Naughton et al. | 6,451,059 | B1 | 9/2002 | Janas et al. |
| 5,522,898 | A | 6/1996 | Bao | 6,472,210 | B1 | 10/2002 | Holy et al. |
| 5,534,028 | A | 7/1996 | Bao et al. | 6,482,234 | B1 | 11/2002 | Weber et al. |
| 5,541,234 | A | 7/1996 | Unger et al. | 6,531,523 | B1 | 3/2003 | Davankov et al. |
| 5,545,229 | A | 8/1996 | Parsons et al. | 6,533,818 | B1 | 3/2003 | Weber et al. |
| 5,556,429 | A | 9/1996 | Felt | 6,534,084 | B1 | 3/2003 | Vyakarnam et al. |
| 5,556,431 | A | 9/1996 | Buttner-Janz | 6,558,421 | B1 | 5/2003 | Fell et al. |
| 5,578,217 | A | 11/1996 | Unger et al. | 6,602,291 | B1 | 8/2003 | Ray et al. |
| 5,601,562 | A | 2/1997 | Wolf et al. | 6,607,558 | B2 | 8/2003 | Kuras |
| 5,626,861 | A | 5/1997 | Laurencin et al. | 6,610,094 | B2 | 8/2003 | Husson |
| 5,645,592 | A | 7/1997 | Nicolais et al. | 6,629,997 | B2 | 10/2003 | Mansmann |
| 5,656,450 | A | 8/1997 | Boyan et al. | 6,645,248 | B2 | 11/2003 | Casutt |
| 5,658,329 | A | 8/1997 | Purkait | 6,667,049 | B2 | 12/2003 | Janas et al. |
| 5,674,241 | A | 10/1997 | Bley et al. | 6,686,437 | B2 | 2/2004 | Buchman et al. |
| 5,674,295 | A | 10/1997 | Ray et al. | 6,707,558 | B2 | 3/2004 | Bennett |
| 5,674,296 | A | 10/1997 | Bryan et al. | 6,710,126 | B1 | 3/2004 | Hirt et al. |
| 5,688,459 | A | 11/1997 | Mao et al. | 6,726,721 | B2 | 4/2004 | Stoy et al. |
| 5,700,289 | A | 12/1997 | Breitbart et al. | 6,733,533 | B1 | 5/2004 | Lozier |
| 5,705,780 | A | 1/1998 | Bao | 6,734,000 | B2 | 5/2004 | Chin et al. |
| 5,716,416 | A | 2/1998 | Lin | 6,740,118 | B2 | 5/2004 | Eisermann et al. |
| 5,750,585 | A | 5/1998 | Park et al. | 6,773,713 | B2 | 8/2004 | Bonassar et al. |
| 5,766,618 | A | 6/1998 | Laurencin et al. | 6,783,546 | B2 | 8/2004 | Zucherman et al. |
| 5,769,897 | A | 6/1998 | Harle | 6,800,298 | B1 | 10/2004 | Burdick et al. |
| 5,789,464 | A | 8/1998 | Muller | 6,802,863 | B2 | 10/2004 | Lawson et al. |
| 5,795,353 | A | 8/1998 | Felt | 6,827,743 | B2 | 12/2004 | Eisermann et al. |
| 5,824,093 | A | 10/1998 | Ray et al. | 6,840,960 | B2 | 1/2005 | Bubb |
| 5,824,094 | A | 10/1998 | Serhan et al. | 6,849,092 | B2 | 2/2005 | Van Dyke et al. |
| 5,844,016 | A | 12/1998 | Sawhney et al. | 6,855,743 | B1 | 2/2005 | Gvozdic |
| 5,847,046 | A | 12/1998 | Jiang et al. | 6,875,232 | B2 | 4/2005 | Nigam |
| 5,855,610 | A | 1/1999 | Vacanti et al. | 6,875,386 | B1 | 4/2005 | Ward et al. |
| 5,863,297 | A | 1/1999 | Walter et al. | 6,875,442 | B2 | 4/2005 | Holy et al. |
| 5,863,551 | A | 1/1999 | Woerly | 6,878,384 | B2 | 4/2005 | Cruise et al. |
| 5,876,452 | A | 3/1999 | Athanasious et al. | 6,881,228 | B2 | 4/2005 | Zdeblick et al. |
| 5,876,741 | A | 3/1999 | Ron | 6,893,463 | B2 | 5/2005 | Fell |
| 5,880,216 | A | 3/1999 | Tanihara et al. | 6,893,466 | B2 | 5/2005 | Trieu |
| 5,900,245 | A | 5/1999 | Sawhney et al. | 6,923,811 | B1 | 8/2005 | Carl et al. |
| 5,916,585 | A | 6/1999 | Cook et al. | 6,960,617 | B2 | 11/2005 | Omidian et al. |
| 5,925,626 | A | 7/1999 | Della Valle et al. | 6,982,298 | B2 | 1/2006 | Calabro et al. |
| 5,928,239 | A | 7/1999 | Mirza | 6,993,406 | B1 | 1/2006 | Cesarano, III et al. |
| 5,935,129 | A | 8/1999 | McDevitt et al. | 7,008,635 | B1 | 3/2006 | Coury et al. |
| 5,944,754 | A | 8/1999 | Vacanti | 7,012,034 | B2 | 3/2006 | Heide et al. |
| 5,947,844 | A | 9/1999 | Shimosaka et al. | 7,022,522 | B2 | 4/2006 | Guan et al. |
| 5,948,829 | A | 9/1999 | Wallajapet et al. | 7,048,766 | B2 | 5/2006 | Ferree |
| 5,957,787 | A | 9/1999 | Hwang | 7,052,515 | B2 | 5/2006 | Simonson |
| 5,976,186 | A | 11/1999 | Bao et al. | 7,060,097 | B2 | 6/2006 | Fraser et al. |
| 5,981,826 | A | 11/1999 | Ku et al. | 7,066,958 | B2 | 6/2006 | Ferree |
| 6,001,352 | A | 12/1999 | Boyan et al. | 7,066,960 | B1 | 6/2006 | Dickman |
| 6,027,744 | A | 2/2000 | Vacanti et al. | 7,083,649 | B2 | 8/2006 | Zucherman et al. |
| 6,060,534 | A | 5/2000 | Ronan et al. | 7,091,191 | B2 | 8/2006 | Laredo et al. |
| 6,093,205 | A | 7/2000 | McLeod et al. | 7,156,877 | B2 | 1/2007 | Lotz et al. |
| 6,102,954 | A | 8/2000 | Albrektsson et al. | 7,186,419 | B2 | 3/2007 | Petersen |
| 6,103,255 | A | 8/2000 | Levene et al. | 7,201,774 | B2 | 4/2007 | Ferree |
| 6,132,465 | A | 10/2000 | Ray et al. | 7,201,776 | B2 | 4/2007 | Ferree et al. |
| 6,156,067 | A | 12/2000 | Bryan et al. | 7,214,245 | B1 | 5/2007 | Marcolongo et al. |
| 6,171,610 | B1 | 1/2001 | Vacanti et al. | 7,217,294 | B2 | 5/2007 | Kusanagi et al. |
| | | | | 7,235,592 | B2 | 6/2007 | Muratoglu et al. |

US 8,486,436 B2

Page 3

| | | | | | | | |
|--------------|------|---------|----------------------|--------------|----|---------|-----------------------|
| 7,250,060 | B2 | 7/2007 | Trieu | 2005/0177238 | A1 | 8/2005 | Khandkar et al. |
| 7,258,692 | B2 | 8/2007 | Thelen et al. | 2005/0209704 | A1 | 9/2005 | Maspero et al. |
| 7,264,634 | B2 | 9/2007 | Schmieding | 2005/0216087 | A1 | 9/2005 | Zucherman et al. |
| 7,282,165 | B2 | 10/2007 | Williams, III et al. | 2005/0228500 | A1 | 10/2005 | Kim et al. |
| 7,291,169 | B2 | 11/2007 | Hodorek | 2005/0233454 | A1 | 10/2005 | Nies et al. |
| 7,316,919 | B2 | 1/2008 | Childs et al. | 2005/0244449 | A1 | 11/2005 | Sayer et al. |
| 7,332,117 | B2 | 2/2008 | Higham et al. | 2005/0260178 | A1 | 11/2005 | Vandenburgh et al. |
| 7,357,798 | B2 | 4/2008 | Sharps et al. | 2005/0261682 | A1 | 11/2005 | Ferree |
| 7,377,942 | B2 | 5/2008 | Berry | 2005/0273176 | A1 | 12/2005 | Ely et al. |
| 7,682,540 | B2 * | 3/2010 | Boyan et al. | 2005/0277921 | A1 | 12/2005 | Eisermann et al. |
| 7,828,853 | B2 | 11/2010 | Ek et al. | 2005/0278025 | A1 | 12/2005 | Ku et al. |
| 7,910,124 | B2 * | 3/2011 | Boyan et al. | 2005/0287187 | A1 | 12/2005 | Mansmann |
| 8,002,830 | B2 * | 8/2011 | Boyan et al. | 2006/0002890 | A1 | 1/2006 | Hersel et al. |
| 8,142,808 | B2 * | 3/2012 | Boyan et al. | 2006/0052874 | A1 | 3/2006 | Johnson et al. |
| 8,318,192 | B2 | 11/2012 | Boyan et al. | 2006/0052875 | A1 | 3/2006 | Bernero et al. |
| 2001/0029399 | A1 | 10/2001 | Ku | 2006/0052878 | A1 | 3/2006 | Schmieding |
| 2001/0038831 | A1 | 11/2001 | Park et al. | 2006/0058413 | A1 | 3/2006 | Leistner et al. |
| 2001/0046488 | A1 | 11/2001 | Vandenburgh et al. | 2006/0064172 | A1 | 3/2006 | Trieu |
| 2002/0026244 | A1 | 2/2002 | Trieu | 2006/0064173 | A1 | 3/2006 | Guederian |
| 2002/0031500 | A1 | 3/2002 | MacLaughlin et al. | 2006/0083728 | A1 | 4/2006 | Kusanagi et al. |
| 2002/0034646 | A1 | 3/2002 | Canham | 2006/0100304 | A1 | 5/2006 | Vresilovic et al. |
| 2002/0072116 | A1 | 6/2002 | Bhatia et al. | 2006/0121609 | A1 | 6/2006 | Yannas et al. |
| 2002/0140137 | A1 | 10/2002 | Sapieszko et al. | 2006/0122706 | A1 | 6/2006 | Lo |
| 2002/0173855 | A1 | 11/2002 | Mansmann | 2006/0136064 | A1 | 6/2006 | Sherman |
| 2002/0183845 | A1 | 12/2002 | Mansmann | 2006/0136065 | A1 | 6/2006 | Gontarz et al. |
| 2002/0183848 | A1 | 12/2002 | Ray et al. | 2006/0200250 | A1 | 9/2006 | Ku |
| 2002/0187182 | A1 | 12/2002 | Kramer et al. | 2006/0206209 | A1 | 9/2006 | Cragg et al. |
| 2003/0008395 | A1 | 1/2003 | Holy et al. | 2006/0224244 | A1 | 10/2006 | Thomas et al. |
| 2003/0008396 | A1 | 1/2003 | Ku | 2006/0229721 | A1 | 10/2006 | Ku |
| 2003/0021823 | A1 | 1/2003 | Landers et al. | 2006/0235541 | A1 | 10/2006 | Hodorek |
| 2003/0055505 | A1 | 3/2003 | Sicotte et al. | 2006/0257560 | A1 | 11/2006 | Barone et al. |
| 2003/0059463 | A1 | 3/2003 | Lahtinen | 2006/0259144 | A1 | 11/2006 | Trieu |
| 2003/0082808 | A1 | 5/2003 | Guan et al. | 2006/0282165 | A1 | 12/2006 | Pisharodi |
| 2003/0175656 | A1 | 9/2003 | Livne et al. | 2006/0282166 | A1 | 12/2006 | Molz et al. |
| 2003/0176922 | A1 | 9/2003 | Lawson et al. | 2006/0287730 | A1 | 12/2006 | Segal et al. |
| 2003/0199984 | A1 | 10/2003 | Trieu | 2006/0293561 | A1 | 12/2006 | Abay |
| 2003/0220695 | A1 | 11/2003 | Sevrain | 2006/0293751 | A1 | 12/2006 | Lotz et al. |
| 2003/0233150 | A1 | 12/2003 | Bourne et al. | 2007/0010889 | A1 | 1/2007 | Francis |
| 2004/0010048 | A1 | 1/2004 | Evans et al. | 2007/0014867 | A1 | 1/2007 | Kusanagi et al. |
| 2004/0024465 | A1 | 2/2004 | Lambrecht et al. | 2007/0032873 | A1 | 2/2007 | Pisharodi |
| 2004/0044412 | A1 | 3/2004 | Lambrecht et al. | 2007/0038301 | A1 | 2/2007 | Hudgins |
| 2004/0052867 | A1 | 3/2004 | Canham | 2007/0043441 | A1 | 2/2007 | Pisharodi |
| 2004/0059415 | A1 | 3/2004 | Schmieding | 2007/0067036 | A1 | 3/2007 | Hudgins et al. |
| 2004/0059425 | A1 | 3/2004 | Schmieding | 2007/0073402 | A1 | 3/2007 | Vresilovic et al. |
| 2004/0063200 | A1 | 4/2004 | Chaikof et al. | 2007/0093906 | A1 | 4/2007 | Hudgins et al. |
| 2004/0064195 | A1 | 4/2004 | Herr | 2007/0106387 | A1 | 5/2007 | Marcolongo et al. |
| 2004/0073312 | A1 | 4/2004 | Eisermann et al. | 2007/0116678 | A1 | 5/2007 | Sung et al. |
| 2004/0092653 | A1 | 5/2004 | Ruberti et al. | 2007/0118218 | A1 | 5/2007 | Hooper |
| 2004/0117022 | A1 | 6/2004 | Marnay et al. | 2007/0118225 | A1 | 5/2007 | Hestad et al. |
| 2004/0143327 | A1 | 7/2004 | Ku | 2007/0134333 | A1 | 6/2007 | Thomas et al. |
| 2004/0143329 | A1 | 7/2004 | Ku | 2007/0135922 | A1 | 6/2007 | Trieu |
| 2004/0143333 | A1 | 7/2004 | Bain et al. | 2007/0142326 | A1 | 6/2007 | Shue |
| 2004/0147016 | A1 | 7/2004 | Rowley et al. | 2007/0162135 | A1 | 7/2007 | Segal et al. |
| 2004/0171143 | A1 | 9/2004 | Chin et al. | 2007/0164464 | A1 | 7/2007 | Ku |
| 2004/0172135 | A1 | 9/2004 | Mitchell | 2007/0167541 | A1 | 7/2007 | Ruberti et al. |
| 2004/0220296 | A1 | 11/2004 | Lowman et al. | 2007/0168039 | A1 | 7/2007 | Trieu |
| 2004/0220669 | A1 | 11/2004 | Studer | 2007/0173951 | A1 | 7/2007 | Wijlaars et al. |
| 2004/0220670 | A1 | 11/2004 | Eisermann et al. | 2007/0179606 | A1 | 8/2007 | Huyghe et al. |
| 2004/0249465 | A1 | 12/2004 | Ferree | 2007/0179614 | A1 | 8/2007 | Heinz et al. |
| 2005/0037052 | A1 | 2/2005 | Udipi et al. | 2007/0179615 | A1 | 8/2007 | Heinz et al. |
| 2005/0043733 | A1 | 2/2005 | Eisermann et al. | 2007/0179617 | A1 | 8/2007 | Brown et al. |
| 2005/0043802 | A1 | 2/2005 | Eisermann et al. | 2007/0179618 | A1 | 8/2007 | Trieu et al. |
| 2005/0049706 | A1 | 3/2005 | Brodke et al. | 2007/0179620 | A1 | 8/2007 | Seaton, Jr. et al. |
| 2005/0055094 | A1 | 3/2005 | Kuslich | 2007/0179621 | A1 | 8/2007 | McClellan, III et al. |
| 2005/0055099 | A1 | 3/2005 | Ku | 2007/0179622 | A1 | 8/2007 | Denoziere et al. |
| 2005/0071003 | A1 | 3/2005 | Ku | 2007/0196454 | A1 | 8/2007 | Stockman et al. |
| 2005/0074877 | A1 | 4/2005 | Mao | 2007/0202074 | A1 | 8/2007 | Shalaby |
| 2005/0079200 | A1 | 4/2005 | Rathenow et al. | 2007/0203095 | A1 | 8/2007 | Sadozai et al. |
| 2005/0090901 | A1 | 4/2005 | Studer | 2007/0203580 | A1 | 8/2007 | Yeh |
| 2005/0096744 | A1 | 5/2005 | Trieu et al. | 2007/0208426 | A1 | 9/2007 | Trieu |
| 2005/0106255 | A1 | 5/2005 | Ku | 2007/0213718 | A1 | 9/2007 | Trieu |
| 2005/0137677 | A1 | 6/2005 | Rush | 2007/0213822 | A1 | 9/2007 | Trieu |
| 2005/0137707 | A1 | 6/2005 | Malek | 2007/0213823 | A1 | 9/2007 | Trieu |
| 2005/0143826 | A1 | 6/2005 | Zucherman et al. | 2007/0213824 | A1 | 9/2007 | Trieu |
| 2005/0149196 | A1 | 7/2005 | Zucherman et al. | 2007/0213825 | A1 | 9/2007 | Thramann |
| 2005/0154462 | A1 | 7/2005 | Zucherman et al. | 2007/0224238 | A1 | 9/2007 | Mansmann et al. |
| 2005/0154463 | A1 | 7/2005 | Trieu | 2007/0225823 | A1 | 9/2007 | Hawkins et al. |
| 2005/0169963 | A1 | 8/2005 | Van Dyke et al. | 2007/0227547 | A1 | 10/2007 | Trieu |
| 2005/0171608 | A1 | 8/2005 | Peterman et al. | 2007/0233259 | A1 | 10/2007 | Muhanna et al. |

2007/0265626 A1 11/2007 Seme
 2007/0270876 A1 11/2007 Kuo et al.
 2007/0270970 A1 11/2007 Trieu
 2007/0270971 A1 11/2007 Trieu et al.
 2007/0299540 A1 12/2007 Ku
 2008/0004707 A1 1/2008 Cragg et al.
 2008/0015697 A1 1/2008 McLeod et al.
 2008/0021563 A1 1/2008 Chudzik
 2008/0031962 A1 2/2008 Boyan et al.
 2008/0045949 A1 2/2008 Hunt et al.
 2008/0051889 A1 2/2008 Hodorek
 2008/0057128 A1 3/2008 Li et al.
 2008/0075657 A1 3/2008 Abrahams et al.
 2008/0077242 A1 3/2008 Reo et al.
 2008/0077244 A1 3/2008 Robinson
 2008/0097606 A1 4/2008 Cragg et al.
 2008/0103599 A1 5/2008 Kim et al.
 2008/0114367 A1 5/2008 Meyer
 2008/0125870 A1 5/2008 Carmichael et al.
 2008/0131425 A1 6/2008 Garcia et al.
 2008/0145404 A1 6/2008 Hill et al.
 2008/0166329 A1 7/2008 Sung et al.
 2008/0279941 A1 11/2008 Boyan et al.
 2008/0279943 A1 11/2008 Boyan et al.
 2009/0182421 A1 7/2009 Silvestrini et al.
 2009/0263446 A1 10/2009 Boyan et al.
 2010/0198258 A1 8/2010 Heaven et al.
 2011/0040332 A1 2/2011 Culbert et al.
 2011/0172771 A1 7/2011 Boyan et al.

FOREIGN PATENT DOCUMENTS

EP 0222407 A2 5/1987
 EP 0346129 A1 12/1989
 EP 0505634 A1 9/1992
 EP 0410010 B1 10/1993
 EP 0411105 B1 6/1995
 EP 0845480 A1 6/1998
 EP 0919209 A1 6/1999
 EP 1287796 A1 3/2003
 EP 1030697 B1 8/2003
 EP 1344538 A1 9/2003
 EP 1584338 A2 10/2005
 EP 1482996 B1 11/2005
 GB 02056882 A 3/1981
 GB 02128501 A 5/1984
 JP 02-184580 7/1990
 JP 04053843 2/1992
 JP 07247365 9/1995
 JP 11035732 2/1999
 JP 2005-199054 7/2005
 JP 2006-101893 4/2006
 WO WO90/07545 A2 7/1990
 WO WO90/07575 A1 7/1990
 WO WO90/10018 A1 9/1990
 WO WO93/16664 A1 9/1992
 WO WO94/01483 A1 1/1994
 WO WO95/25183 A1 9/1995
 WO WO97/06101 A1 2/1997
 WO WO97/46178 A1 12/1997
 WO WO98/02146 A2 1/1998
 WO WO98/50017 A1 11/1998
 WO WO99/25391 A2 5/1999
 WO WO99/34845 A1 7/1999
 WO WO00/30998 A1 6/2000
 WO WO00/42991 A1 7/2000
 WO WO00/62829 A1 10/2000
 WO WO00/66191 11/2000
 WO WO01/02033 A1 1/2001
 WO WO01/22902 A2 4/2001
 WO WO01/59160 A1 8/2001
 WO WO01/64030 A1 9/2001
 WO WO01/70436 A1 9/2001
 WO WO01/91822 A1 12/2001
 WO WO02/09647 A2 2/2002
 WO WO02/30480 A1 4/2002
 WO WO02/064182 A3 8/2002
 WO WO03/030787 A1 4/2003
 WO WO03/092760 A1 11/2003
 WO WO2004/060554 A1 7/2004

WO WO2004/101013 A1 11/2004
 WO WO2005/077304 A1 8/2005
 WO WO2005/097006 A2 10/2005
 WO WO2006/018531 A2 2/2006
 WO WO2006/019634 A1 2/2006
 WO WO2006/030054 A1 3/2006
 WO WO2006/034365 A2 3/2006
 WO WO2005/077013 A2 8/2006

OTHER PUBLICATIONS

Chen et al., "Boundary layer infusion of heparin prevents thrombosis and reduces neointimal hyperplasia in venous polytetrafluoroethylene grafts without system anticoagulation," J. Vascular Surgery, 22:237-247 (1995).
 Chu et al., "Polyvinyl Alcohol Cryogel: An Ideal Phantom Material for MR Studies of Arterial Elasticity," Magnetic Resonance in Medicine, v. 37, pp. 314-319 (1997).
 Hickey et al., "Mesh size and diffusive characteristics of semicrystalline poly(vinyl alcohol) membranes prepared by freezing/thawing techniques," Journal of Membrane Science, 107(3), pp. 229-237 (1995).
 Hoffman et al., "Interactions of Blood and Blood Components at Hydrogel Interfaces," Ann. New York Acad. Sci., 283:372-382 (1977).
 Hunt, Knee Simulation, Creep, and Friction Tests of Poly(Vinyl Alcohol) Hydrogels Manufactured Using Injection Molding and Solution Casting, Thesis for M.S., University of Notre Dame (Jul. 2006).
 Katta et al., "Friction and wear behavior of poly(vinyl alcohol)/poly(vinyl pyrrolidone) hydrogels for articular cartilage replacement," Journal of Biomedical Materials Research, vol. 83A, pp. 471-479 (2007).
 Kieswetter et al., "The Role of Implant Surface Characteristics in the Healing of Bone," Crit. Rev. Oral Biol. Med., 7(4):329-345 (1996).
 Kieswetter et al., "Surface roughness modulates the local production of growth factors and cytokines by osteoblast-like MG-63 cells," Journal of Biomedical Materials Research, vol. 32, pp. 55-63 (1996).
 Kobayashi et al., "Characterization of a polyvinyl alcohol-hydrogel artificial articular cartilage prepared by injection molding," J. Biomater. Sci. Polymer Edn., 15(6): 741-751 (2003).
 Kobayashi et al., "Development of an artificial meniscus using polyvinyl alcohol-hydrogel for early return to, and continuance of, athletic life in sportspersons with severe meniscus injury. I: mechanical evaluation," The Knee, 10 (2003); 47-51.
 Kohavi et al., "Markers of primary mineralization are correlated with bone-bonding ability of titanium or stainless steel in vivo," Clin. Oral. Impl. Res., 6:1-13 (1995).
 Koutsopoulos et al., "Calcification of porcine and human cardiac valves: testing of various inhibitors for antimicrobialization," J. Mater. Sci. Mater. Med., 9:421-424 (1998).
 Kwak, BK, et al., "Chitin-based Embolic Materials in the Renal Artery of Rabbits: Pathologic Evaluation of an Absorbable Particulate Agent", Radiology, 236:151-158 (2005).
 Landolt et al., "Electrochemical micromachining, polishing and surface structuring of metals: fundamental aspects and new developments", Elsevier Science Ltd., pp. 3185-3201 (2003), Electrochimica Acta vol. 48.
 Lazzeri et al., "Physico-chemical and mechanical characterization of hydrogels of poly(vinyl alcohol) and hyaluronic acid," J. Mater. Sci. In Med., 5:862-867 (1994).
 Liao et al., "Response of rat osteoblast-like cells to microstructured model surfaces in vitro," Biomaterials, 24, pp. 649-654 (2003).
 Lozinsky et al., "Study of cryostructurization of polymer systems. VII. Structure formation under freezing of poly(vinyl alcohol) aqueous solutions," Colloid & Polymer Science, vol. 264, pp. 19-24 (1986).
 Lozinsky et al., "Study of Cryostructuration of Polymer Systems. XII. Poly(vinyl alcohol) Cryogels: Influence of Low-Molecular Electrolytes," Journal of Applied Polymer Science, vol. 61, pp. 1991-1998 (1996).
 Lozinsky et al., "Study of Cryostructuration of Polymer Systems. XI. The Formation of PVA Cryogels by Freezing-Thawing the Polymer Aqueous Solutions Containing Additives of Some Polyols," Journal of Applied Polymer Science, vol. 58, pp. 171-177 (1995).

- Lozinsky et al., "Poly(vinyl alcohol) cryogels employed as matrices for cell immobilization. 2. Entrapped cells resemble porous fillers in their effects on the properties of PVA-cryogel carrier," *Enzyme and Microbial Technology*, vol. 20, No. 3, pp. 182-190 (1997).
- Lozinsky et al., "Poly(vinyl alcohol) cryogels employed as matrices for cell immobilization. 3. Overview of recent research and developments," *Enzyme and Microbial Technology*, vol. 23, No. 3-4, pp. 227-242 (1998).
- Lusta et al., "Immobilization of fungus *Aspergillus* sp. by a novel cryogel technique for production of extracellular hydrolytic enzymes", *Process Biochemistry*, vol. 35, pp. 1177-1182 (2000).
- Ma et al., "Friction Properties of novel PVP/PVA blend hydrogels as artificial cartilage," *Journal of Biomedical Materials Research*, vol. 93A, pp. 1016-1019 (2010).
- Martin et al., "Effect of titanium surface roughness on proliferation, differentiation, and protein synthesis of human osteoblast-like cells (MG63)," *Journal of Biomedical Materials Research*, vol. 29, pp. 389-401 (1995).
- Nagura et al., "Structure of poly(vinyl alcohol) hydrogel prepared by repeated freezing and melting," *Polymer*, 30:762-765 (1989).
- Nakashima et al., "Study on Wear Reduction Mechanisms of Artificial Cartilage by Synergistic Protein Boundary Film Formation," *Japan Soc'y of Mech. Eng'r Int'l J., Series C*, vol. 48, No. 4, pp. 555-561 (2005).
- Oka et al., "Development of an Artificial Articular Cartilage", *Clinical Materials*, vol. 6, pp. 361-381 (1990).
- Ong et al., "Osteoblast Responses to BMP-2-Treated Titanium in Vitro," *The International Journal of Oral & Maxillofacial Implants*, vol. 12, No. 5, pp. 649-654 (1997).
- Peppas et al., "Reinforced uncrosslinked poly(vinyl alcohol) gels produced by cyclic freezing-thawing processes: a short review," *Journal of Controlled Release*, 16(3): 305-310 (1991).
- Peppas et al., "Structure of Hydrogels by Freezing-Thawing Cyclic Processing," *Bulletin of the American Physical Society*, 36:582 (1991).
- Peppas et al., "Controlled release from poly(vinyl alcohol) gels prepared by freezing-thawing processes," *Journal of Controlled Release*, vol. 18, pp. 95-100 (1992).
- Peppas et al., "Ultrapure poly(vinyl alcohol) hydrogels with mucoadhesive drug delivery characteristics," *European Journal of Pharmaceutics and Biopharmaceutics*, 43(1): 51-58 (1997).
- Ratner et al., *Biomaterials Science an Introduction to Materials in Medicine*, Academic Press, pp. 52, 53, & 62 (1996).
- Ricciardi et al., "Structure and Properties of Poly(vinyl alcohol) Hydrogels Obtained by Freeze/Thaw Techniques," *Macromol. Symp.*, 222: 49-63 (2005).
- Schwartz et al., "Underlying Mechanisms at the Bone-Biomaterial Interface," *Journal of Cellular Biochemistry*, 56:340-347 (1994).
- Singh et al., "Polymeric Hydrogels: Preparation and Biomedical Applications," *J. Sci. Ind. Res.*, 39:162-171 (1980).
- Stauffer et al., "Poly(vinyl alcohol) hydrogels prepared by freezing-thawing cyclic processing," *Polymer* 33(1818):3932-3936 (1992).
- Stewart et al., "Protein release from PVA gels prepared by freezing and thawing techniques," *Proc. Int. Symp. Controlled Release Bioact. Mater.*, 26th, 1004-1005 (1999).
- Szczesna-Antezak et al., "*Bacillus subtilis* cells immobilised in PVA-cryogels," *Biomolecular Engineering*, vol. 17, pp. 55-63 (2001).
- The American Heritage® Science Dictionary [online], Houghton Mifflin Company, 2002 [retrieved on Jun. 3, 2008]. Retrieved from the internet: <URL: <http://dictionary.reference.com/browse/pore>>, pp. 1-8 of 8.
- Watase et al., "Rheological and DSC Changes in Poly(vinyl alcohol) Gels Induced by Immersion in Water," *Journal of Polymer Science, Polym. Phys. Ed.*, 23(9): 1803-1811 (1985).
- Watase et al., "Thermal and rheological properties of poly(vinyl alcohol) hydrogels prepared by repeated cycles of freezing and thawing," *Makromol. Chem.*, v. 189, pp. 871-880 (1988).
- Willcox et al., "Microstructure of Poly(vinyl alcohol) Hydrogels Produced by Freeze/Thaw Cycling," *Journal of Polymer Sciences: Part B: Polymer Physics*, vol. 37, pp. 3438-3454 (1999).
- WordNet® 3.0 [online], Princeton University, 2006 [retrieved on Aug. 6, 2008]. Retrieved from the Internet: <URL: <http://dictionary.reference.com/browse/mesh>>.
- Yamaura et al., "Properties of Gels Obtained by Freezing/Thawing of Poly(vinyl Alcohol)/Water/Dimethyl Sulfoxide Solutions," *J. Appl. Polymer Sci.*, 37:2709-2718 (1989).
- Yokoyama et al., "Morphology and structure of highly elastic poly(vinyl alcohol) hydrogel prepared by repeated freezing-and-melting," *Colloid & Polymer Science*, vol. 264, No. 7, pp. 595-601 (1986).
- Zheng-Qiu et al., "The development of artificial articular cartilage—PVA-hydrogel," *Bio-Medical Materials and Engineering*, vol. 8, pp. 75-81 (1998).

* cited by examiner




Figure 1

Figure 2




Figure 3




Figure 4





Figure 5






Figure 6

ARTICULAR JOINT IMPLANT

CROSS REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 12/117,673, filed May 8, 2008, which is a continuation of U.S. patent application Ser. No. 11/053,410, filed Feb. 7, 2005 and issued on Aug. 23, 2011 as U.S. Pat. No. 8,002,830, which claims the benefit of U.S. Provisional Patent Application Ser. No. 60/542,514, filed Feb. 6, 2004, the entireties of all of which are incorporated by reference herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to the use of surface modified biocompatible materials to promote the attachment of bone or bone-like cells to an implant surface. The surface of the biomaterials, which may include hydrogels, when modified in accordance with the description herein, directs the cells that migrate to the implant site to differentiate into cells that attach and lay down bone or bone-derivative material, or cartilage or cartilaginous material further enhancing the biocompatibility of the implanted device.

2. Background Art

Materials used in the construction of implantable medical devices must be nontoxic, nonantigenic, and noninflammatory. Hydrogels are a preferred type of polymeric material for implantable devices. Because of their high water content, analogous to living tissue, they are superior in biocompatibility to non-hydrous polymeric materials.

U.S. Pat. No. 5,981,826, issued to Ku et al., describes the preparation of polyvinyl alcohol hydrogels (PVA-H) by physically crosslinking an aqueous solution of polyvinyl alcohol (PVA) to produce a gel. The crosslinking is accomplished by subjecting the aqueous PVA solution to multiple cycles of freezing and thawing. One limitation of the prior art is that the hydrogels produced are relatively nonporous and the pore size and degree of porosity, that is the density of the pores within the hydrogel, cannot vary independently of the mechanical properties or stiffness of the hydrogel.

Methods for producing certain porous hydrogels also exist in the art. U.S. Pat. No. 6,268,405 issued to Yao et al., describes methods for creating porous PVA-Hs by including immiscible materials in the polymerization process. After the hydrogel is polymerized, the included immiscible materials are washed out of the hydrogel by an appropriate solvent, yielding pores which are broadly distributed throughout the hydrogel. Controlling the size and density of the pores is accomplished by varying the molecular weight of the immiscible materials. A disadvantage of Yao et al. is that the range of attainable pore sizes is limited. Moreover, the invention of Yao et al. is limited in that it can only produce hydrogels whose pores extend throughout the hydrogel. The pores in Yao et al. are intended to create vascularization of the hydrogel in soft or non-load bearing tissue. A further disadvantage of Yao et al. is that the pore sizes are broadly distributed about the average pore size.

In addition to crosslinking by physical means, hydrogels may be chemically crosslinked using, for example, methods similar to those described by Müller in U.S. Pat. No. 5,789,464. Similarly, chemical crosslinking or polymerization methods may also be used to adhere hydrogels to surfaces, including biological tissues. U.S. Pat. No. 5,900,245, issued to Sawhney et al., describes applications of these techniques. These and other methods for the crosslinking or further poly-

merization of hydrogels are derived from methods used in the polymer industry and are well known in the art.

Artificial discs intended for the replacement of a damaged intervertebral disc have been described. These are typically articulated devices comprising two rigid metal plates adhered to opposite ends of an elastomeric core. In use, the artificial disc is placed in the intervertebral space and the metal plates are secured to the surfaces of adjacent vertebrae. Various embodiments of artificial discs of this type are described in U.S. Pat. Nos. 5,674,296 and 6,156,067, issued to Bryan et al., U.S. Pat. No. 5,824,094, issued to Serhan et al., U.S. Pat. No. 6,402,785, issued to Zdeblick et al. More recent embodiments, e.g. U.S. Pat. No. 6,419,704, issued to Ferree and U.S. Pat. No. 6,482,234, issued to Weber et al., include descriptions of elastomeric cores that may be formed from materials with different elasticities to better mimic the native structure of spinal discs.

The disadvantages of the artificial disc devices of the prior art are numerous. These prior art devices require the mechanical attachment of rigid artificial materials, such as titanium, directly to the bone with screws, staples, nails, cement, or other mechanical means. These rigid materials are only minimally compatible with natural, living bone and separation of the implant from the bone is often observed over long-term implantation. In addition, materials used in artificial discs of the prior art have physical and mechanical properties distinctly different from those of natural spinal discs and thus, inadequately duplicate the desired properties of native spinal discs.

Vertebral fusion is still the most commonly performed procedure to treat debilitating pain associated with degenerative spinal disc disease or disc trauma, despite the fact that the procedure has many drawbacks. Vertebral fusion increases stress and strain on the discs adjacent to the fusion site, and it is now widely accepted that fusion is responsible for the accelerated degeneration of adjacent levels. Current multi-component spinal disc prosthesis designs, elastomeric cores with metal plates on both the upper and lower surfaces, are susceptible to problems with interfacial bonding and wear. These designs have shown spontaneous device detachment due to retraction of bone tissue from the metal surface.

Bone ingrowth and attachment in the art has often required the use of bone promoting growth factors. For example, U.S. Pat. No. 5,108,436, issued to Chu et al., describes using a porous implant for use in load bearing bone replacement which is used in combination with an osteogenic factor such as TGF- β .

Biomedical devices which are implanted in or around bone often fail because of fibrinogen encapsulation of the implant instead of cellular attachment to the implant itself. This encapsulation is a defensive reaction attempting to minimize contact between the body and the implant and is considered a sign of implant incompatibility.

Moreover, the art of bone ingrowth to implantable surface contains a multitude of examples relating to porous directed ingrowth where bone essentially grows into and around channels of the implant. For example, U.S. Pat. No. 4,911,720, issued to Collier et al., discusses the ingrowth of bone into interconnecting pores which essentially locks bone into place. This method is disadvantageous in that bone does not actually attach to the material, instead bone attaches to other bone around the implant. In the unfortunate event that an implant must be removed, this type of Collier ingrowth results in large amounts of disruption to the surrounding bone tissue.

SUMMARY OF THE INVENTION

The present invention describes a biomaterial for implantation into the body. The biomaterial, which can be a hydro-

gel, possesses a textured surface which is comprised of superficial surface pores. Stated differently, the pores on the surface of the hydrogel substrate do not extend throughout the hydrogel but instead remain within a region near the surface. The hydrogel substrate can be comprised of two or more pore sizes. Specifically, the pores of the first size each have a diameter of between 3 and 1000 micrometers, preferably between 10 and 300 micrometers, and preferably between 30 and 100 micrometers. Further, the pores of the second size would each have a diameter of between 0.5 to 20 micrometers, preferably between 1 to 10 micrometers, and preferably between 2 and 5 micrometers. One embodiment of the present invention provides the second, smaller pores disposed within the first, larger pores. The superficial pores of the present invention extend into the hydrogel substrate less than 1 millimeter, preferably 500 micrometers, and preferably 200 micrometers, from the surface. The hydrogel substrate of the present embodiment can comprise polyvinyl alcohol having a water content of at least 5% and preferably at least 30%.

The present invention is also drawn to a hydrogel substrate comprising a hydrogel surface having thereon a plurality of first substantially uniform superficial pores and a unique plurality of second substantially uniform superficial pores. This hydrogel can possess two different yet substantially uniform superficial pore sizes grouped into a first, larger pore size and a second, smaller pore size. The pores of one size are substantially uniform in diameter relative to the other pores of the same size. Specifically, the first pores have an average diameter of between 2 and 600 micrometers, preferably between 5 and 200 micrometers, and preferably between 20 and 60 micrometers. Further, the second pores have an average diameter of between 0.1 and 10 micrometers, preferably between 0.2 to 5 micrometers, and preferably between 0.5 to 2 micrometers. The superficial pores of the present invention can be arranged so that the smaller, second pores are within the larger, first pores. The superficial pores of the present invention extend into the hydrogel substrate less than 1 millimeter, preferably no more than 500 micrometers, and preferably no more than 200 micrometers. The hydrogel substrate of the present embodiment can be made up of polyvinyl alcohol having a water content of at least 5% and preferably at least 30% w/w of the overall hydrogel.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a spinal disc replacement device made in accordance with one embodiment of the present invention.

FIG. 2 is an example of a superficial surface pore construct exemplary of one embodiment of the present invention.

FIG. 3 are multiple types of superficial surface pores embodied by the present invention.

FIG. 4 is a graph of cell proliferation seen on the surfaces of FIG. 3.

FIG. 5 is a graph of increased bone or bone-like cell markers resulting from exposure to the surfaces of FIG. 3.

FIG. 6 is an image of a substrate which has been generated in accordance with the present invention. The upper image is a further magnification of the image in the lower portion of FIG. 6.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is drawn to a biomaterial substrate which may comprise a hydrogel surface having thereon a plurality of first substantially uniform superficial pores and a unique plurality of second substantially uniform superficial pores. Specifically, the pores of the first size preferably each

have a diameter of between 3 and 1000 micrometers, preferably between 10 and 300 micrometers, and preferably between 30 and 100 micrometers, including without limitation, pores with a cross-section of 30, 40, 50, 60, 70, 80, 90, and 100 micrometers. Further, the pores of the second size preferably each have a diameter of between 0.5 to 20 micrometers, preferably between 1 to 10 micrometers, and preferably between 2 and 5 micrometers, including without limitation, pores with a cross-section of 0.5, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, and 20 micrometers. It should be readily apparent to one of ordinary skill in the art that the use of the term diameter also would encompass the cross-section of the pore when not a perfect circle. In fact, the term "pore" should not be read to be limited to circular or spherical shapes. Squares, polygons, triangles, octagons, quadrilaterals, or any other geometric or amorphous structure would perform the function for the invention if properly positioned and sized. One embodiment of the present invention provides the second, smaller pores within the first, larger pores. The invention provides that third, fourth, fifth, and greater substantially uniform pore sizes can be on the hydrogel surface. By substantially uniform it is meant that the pore sizes of a particular class (e.g., first, second, etc.) do not vary more than 10%, preferably the pore sizes of a particular class vary less than 5%, 4%, 3%, more preferably less than 2%, and preferably less than 1% or 0.5%.

The superficial pores of the present invention would extend into the hydrogel substrate no more than 1 millimeter, preferably 500 micrometers, and preferably 200 micrometers, from the surface. The hydrogel substrate of the present embodiment can comprise polyvinyl alcohol having a water content of at least 5% and preferably at least 30% w/w of the overall hydrogel.

The present invention is also drawn to a hydrogel substrate comprising a hydrogel surface having thereon a plurality of first substantially uniform superficial pores and a unique plurality of second substantially uniform superficial pores. This hydrogel substrate can possess two different yet substantially uniform superficial pore sizes grouped into a first, larger pore size and a second, smaller pore size. The pores of one size are substantially uniform in diameter relative to the other pores of the same size. Specifically, the first pores have an average diameter of between 2 and 600 micrometers, preferably between 5 and 200 micrometers, and preferably between 20 and 60 micrometers. Further, the second pores have an average diameter of between 0.1 and 10 micrometers, preferably between 0.2 to 5 micrometers, and preferably between 0.5 to 2 micrometers.

The superficial pores of the present invention can be arranged so that the smaller, second pores are within the larger, first pores. The superficial pores of the present invention can extend into the hydrogel substrate preferably no more than 1 millimeter, preferably no more than 500 micrometers, and preferably no more than 200 micrometers. The hydrogel substrate of the present embodiment can be made up of polyvinyl alcohol having a water content of at least 5% and preferably at least 30% w/w of the overall hydrogel.

In one embodiment of the invention, the superficial pores of the substrate described herein can be arranged in a regular repeating fashion. Such a pattern or waffle structure can be used in embodiments of varying pore size as well as in embodiments where the smaller superficial pores are within the area of the larger superficial pores.

A method provided by the present invention of making a hydrogel substrate possessing a textured surface required by the present invention comprises using an extremely accurate etching technology to generate a mold, pouring a liquid solu-

tion of the hydrogel into the mold, allowing the liquid hydrogel to polymerize and/or crosslink while in the mold, and removing the solid hydrogel substrate from the mold. The extremely accurate etching technology can be MEMS technology or its equivalent. Also, the hydrogel substrate made from this method could be a polyvinyl alcohol hydrogel having a water content of at least 5% and preferably at least 30% w/w of the overall hydrogel.

The present invention also includes a method for making a hydrogel substrate by contacting solid objects with a liquid hydrogel, allowing the hydrogel to polymerize and crosslink while the solid objects are at least partially immersed in the hydrogel, and removing those solid objects from the polymerized and crosslinked hydrogel to form superficial pores therein. The solid objects used to impart the superficial pores may be made of polystyrene beads. Also, the solid objects used to impart the superficial pores may be grit, sand, silicon, silica, and ultra-fine particulate matter. The solid objects used to create the superficial pores can have a diameter of between 3 and 1000 micrometers, preferably between 10 and 300 micrometers, and preferably between 30 and 100 micrometers.

The solid objects used to create the superficial pores of this invention can be removed by use of an organic solvent or other washing means. This hydrogel can be comprised of polyvinyl alcohol possessing a water content of at least 5% w/w of the overall hydrogel.

Accordingly, the present invention is directed to an implantable hydrogel substrate product, a method of making that product, and a method of using that product which substantially improves upon the limitations existing in the art. The invention provides methods of selectively promoting cellular residence and/or differentiation over a surface as described herein. To achieve these and other advantages in accordance with the purpose of the invention, as embodied and broadly described herein, the invention includes a load bearing biocompatible hydrogel for medical implantation that promotes bone attachment. The hydrogel consists of a surface component which has been optimized for implantation. This is accomplished through pores on the surface having a controlled range in distribution of size. The surface pores are superficial and do not extend throughout the hydrogel.

Hydrogels are materials whose state is between that of a solid and of a liquid. Gels consist of polymeric, i.e. long chain, molecules linked together to form a three-dimensional network and are embedded in a liquid medium. In the case of hydrogels, the liquid medium comprises water. The polymer backbone of hydrogels is formed by hydrophilic monomer units and may be neutral or ionic. Examples of neutral and hydrophilic monomer units are ethylene oxide, vinyl alcohol, (meth)acrylamide, N-alkylated (meth)acrylamides, N-methylol(meth)acrylamide, N-vinylamides, N-vinylformamide, N-vinylacetamide, N-vinyl-N-methylacetamide, N-vinyl-N-methylformamide, hydroxyalkyl (meth)acrylates such as hydroxyethylmethacrylate, vinylpyrrolidone, (meth)acrylic esters of polyethylene glycol monoallyl ethers, allyl ethers, of polyethylene glycols, and sugar units such as glucose or galactose. Examples of cationic hydrophilic monomer units are ethyleneimine (in the protonated form), diallyldimethylammonium chloride and trimethylammonium propylmethacrylamide chloride. Examples of anionic monomer units are (meth)acrylic acid, crotonic acid, maleic acid, fumaric acid, itaconic acid, 2-acrylamido-2-methylpropane-sulfonic acid, vinylsulfonic acid, vinylphosphonic acid, 2-methacryloyloxyethanesulfonic acid, 4-vinylbenzene-

sulfonic acid, allylsulfonic acid, vinyltoluenesulfonic acid and vinylbenzenephosphonic acid.

From the example listing above, a hydrogel for use in the present invention may be selected based upon its biocompatibility and stability at various hydration states. For the purposes of the present invention, a suitable hydrogel will have a moisture content of at least 5% w/w of the overall hydrogel, preferably at least 10%, 15%, 20%, 25%, 30%, 35%, 40%, 50%, 60%, 70%, or 80% w/w of the overall hydrogel.

Initial events following implantation of a biomaterial in an orthotopic surgical site include rapid adsorption of serum constituents onto the implant surface. The first cells that are likely to come into contact with the surface are polymorphonuclear cells, platelets, monocytes, and macrophages. These cells release bioactive factors that promote mesenchymal cell migration to the wound site. In addition to these natural factors associated with wound healing, surgeons frequently use bone graft and bone graft substitutes to improve bone formation. Such materials include osteoinductive agents such as demineralized bone matrix and bone morphogenetic protein. If appropriate signals are present mesenchymal cells with an osteoprogenitor phenotype will continue to differentiate into osteoblasts; of these a subset will become osteocytes. Ultimately, the newly formed bone will be remodeled via osteoclastic resorption. The invention provides that physical stimulation of cells via a controllably textured surface contributes to desired cellular differentiation, adhesion, and acceptance of the implant. The present invention also provides that well-known grafting agents may be incorporated into the hydrogel composition, which include, but are not limited to growth factors, angiogenic agents, antibiotics, and the like.

Chemically modified or polar surfaces are generally known to be able to produce more reactive protein adsorption to the implant surface than unmodified or non-polar surfaces. The increased reactivity of the proteins adsorbed onto the polar surface is thought to promote cellular adhesion to that surface. Therefore, the invention provides that the hydrogel composition can possess chemically modified or polar surfaces.

In general, many materials are well-tolerated in bone, but the success of long-term or chronic implantation often depends on the intimacy of the interface between the material surface and the bone. Microarchitecture of the surface is an important determinant of cell response. It has been observed that osteoblast phenotypic expression is surface-dependent. As described herein, specific surface characteristics enhance osteoblast differentiation while permitting proliferation, leading to optimal cell response to the implantation. Likewise, cartilage or cartilage-derivative cells show enhanced differentiation based on surface microarchitecture. Since both bone and cartilage cells are derived from mesenchymal stem cells and have as a common ancestor, osteoprogenitor cells, the present invention refers to bone and bone-like cells to encompass that branch of the differentiation pathway. Stated differently, the present invention provides for the differentiation of bone cells (for example osteocytes, osteoblasts, osteoclasts) as well as bone-like cells (for example chondrocytes or related cartilaginous tissue producing cells).

The mechanical properties of the material must be appropriate for the application. When the mechanical properties of the material are similar to the mechanical properties of the tissue adjacent to the implant, tissue tolerance of the artificial material is enhanced. Polymeric and elastomeric biomaterials can be fabricated with a wide range of mechanical properties, making them suitable for many applications as implantable devices. Because of their high water content, similar to that of

living tissue, hydrogels are superior in biocompatibility to non-hydrous polymeric materials. Polyvinyl alcohol (PVA) is an example of a polymer that can be used to form hydrogels, and has been studied extensively for its potential in biomedical applications. Polyvinyl alcohol hydrogels (PVA-Hs) are biologically well tolerated and compatible with living cartilage tissue.

PVA-Hs can be produced from solution via repeated freezing and thawing cycles that increase the order of the microcrystalline regions, changing the dissolution properties, mesh size, and diffusion properties of the polymer. Also, PVA-Hs can be produced from solution via a slow and sustained transition through the freezing point of the solution. The mechanical properties of PVA-Hs can be varied over a wide range, and stable PVA gels can easily be produced to have an elastic modulus ranging from a few MPa, such as articular cartilage, to about 50 MPa, such as the stiffest portion of the annulus of spinal discs. Increasing the stiffness of a hydrogel can also be achieved through chemical crosslinking. Examples of chemical crosslinker groups are vinyl groups, allyl groups, cinnamates, acrylates, diacrylates, oligoacrylates, methacrylates, dimethacrylates, oligomethacrylates, or other biologically acceptable groups.

Increasing the porosity of a hydrogel substrate produces decreased mechanical strength. When porous hydrogels are used to provide the requisite surface of the present invention, it is advantageous that the porosity not extend throughout the hydrogel, but be limited to a relatively shallow depth below the surface. The thickness of the porous portion of the hydrogel is preferably less than 1 millimeter, less than 500 micrometers, and most preferable less than or equal to 200 micrometers.

The porosity of the hydrogel surface embodied in this invention may be realized in a variety of ways. Molds may be constructed with patterning on the appropriate surfaces of the cavities in the mold. Alternatively, the porosity can be produced by abrasion of a smooth hydrogel surface after molding. Abrading the surface can result in a surface textured such as desired in this invention. Techniques for applying and using abrasives are well known to those of skill in the art.

Using extremely accurate surface building or etching techniques, one can generate extremely intricate surfaces to use as a mold for a surface envisioned by the present invention. Solid free-form fabrication methods offer several unique opportunities for the construction of medical devices. Solid free-form fabrication methods can be used to selectively control composition within the build plane by varying the composition of printed material. This means that unconventional microstructures, such as those with complicated porous networks or unusual gradients, can be designed at a computer-aided design (CAD) terminal and built through a solid free-form process such as three-dimensional printing or MEMS micro-fabrication techniques.

In one embodiment of this invention the molds for casting the hydrogels are created using MEMS micro-fabrication techniques to produce materials with precise repetitive arrays. The microfabrication process uses commercially available, epoxy-based photoresist and standard photolithography masks and techniques to produce the specified surface architecture. The dimensions of features in the x-y plane of the surface are specified by the photomask. The height of the features is dictated by the thickness of the photoresist layer prior to exposure and development. Multiple photoresist layers may be cast and exposed with different masks to build up very complex structures. An example of one such complex feature, with a pseudofractal architecture is shown in the "snowflake" pattern, seen in FIG. 2.

Photolithography is the process of transferring geometric shapes on a mask to the surface of a silicon wafer. The steps involved in the photolithographic process are wafer cleaning; barrier layer formation; photoresist application; soft baking; mask alignment; exposure and development; and hard-baking.

There are two types of photoresist: positive and negative. For positive resists, the resist is exposed with UV light wherever the underlying material is to be removed. In these resists, exposure to the UV light changes the chemical structure of the resist so that it becomes more soluble in the developer. The exposed resist is then washed away by the developer solution, leaving windows of the bare underlying material. The mask, therefore, contains an exact copy of the pattern which is to remain on the wafer.

Negative resists behave in just the opposite manner. Exposure to the UV light causes the negative resist to become polymerized, and more difficult to dissolve. Therefore, the negative resist remains on the surface wherever it is exposed, and the developer solution removes only the unexposed portions. Masks used for negative photoresists, therefore, contain the inverse (or photographic "negative") of the pattern to be transferred.

MEMS fabrication of hydrogel mold surfaces for use in this invention may, for example, involve standard photolithography techniques and epoxy-based photoresists (SU-8 2000 series, MicroChem, Newton, Mass.) in a Class 10 clean-room facility. Photolithography masks can be designed, for example, using a CAD program, or its equivalent, and supplied to order (DuPont Photomasks, Inc., Round Rock, Tex.).

One embodiment of this invention is an artificial intervertebral disc, comprising one or more hydrogels shaped substantially similarly to a natural intervertebral disc. The upper and lower surfaces of the hydrogel, or assembly of hydrogels, are constructed to have a textured surface with a defined level of porosity. That porosity depends primarily upon the size and number of the surface features of the mold used to create the surface texture.

Another embodiment of this invention is a substrate used to repair tissue that has been damaged either chronically or acutely. This substrate can be implanted at a damaged area such as knee cartilage, shoulder bursa repair, or other damaged area one skilled in the art would foresee.

FIG. 1 shows a spinal disc replacement envisioned by the present invention. The spinal disc has an upper portion 1 and a lower portion 2. It is the surfaces of the upper portion 1 and lower portion 2 which possess the textured surface envisioned by the present invention. The upper portion 1 and lower portion 2 will be less elastic and more rigid than the inner region 4 which seeks to mimic the nucleus pulposus. Likewise, the spinal disc may have an intermediate region of elasticity 3 which further aids in the function of the spinal disc. The intermediate region of elasticity 3 may or may not differ from the elasticity of either the inner region 4 or the upper portion 1 or lower portion 2.

The size of the pores comprising the textured surface of the hydrogel can aid in promoting adhesion of one cell type over the other. For example, bone cells can show better attachment and results on textured surfaces where the pores are larger than the pores on a textured surface where cartilage cells attach. The ability to promote bone cells to attach to a given surface as compared to cartilage cells can be considered in the design of an implant. For example, a biomedical implanted device which needs a more rigid attachment to the native bone might require the attachment of bone cells as opposed to cartilage cells, requiring using a surface with larger pores. Likewise, a different implant may need to induce cartilage

development on the surface of the implant and would instead use the textured surface composed of overall smaller pores to enable that selection. Other factors such as the age, sex, and pre-existing medical condition of the patient would be considered depending upon the circumstances.

Conversely, the present invention provides for a hydrogel substrate that can be implanted which possesses multiple regions on that substrate capable of promoting the differentiation and attachment of both bone and bone-like cells such as, for example, osteocytes and chondrocytes. Such a surface would, after the migration of mesenchymal stem cells, promote the differentiation of the mesenchymal stem cell into the osteoprogenitor cell and ultimately into bone and cartilage cells on each type's respective region. Stated differently, the present invention provides for a single hydrogel substrate that has both bone cell promoting regions and cartilage, or bone-like cell, promoting regions.

Osteoblasts assume distinct morphologies depending on the architectural features of their substrate. On microrough surfaces, as long as the peak-to-peak distance is less than the length of the cell body, the cell bodies become more cuboidal, and anchor themselves to the surface through long dendritic filopodia. In contrast, on smoother surfaces osteoblasts flatten and spread, resulting in a fibroblastic appearance. The cell morphology correlates with the physiological behavior of the cells. On smooth surfaces, prostaglandin synthesis is low, TGF- β 1 levels are low, alkaline phosphatase specific activity is low, and osteocalcin levels are low, whereas proliferation rates are relatively high in comparison with cells cultured on rougher surfaces. That is, a greater number of cells may be present on smooth surfaces, but the cells on textured surfaces show greater tendency to proliferate into bone or bone-like cells.

Responsiveness to the surface also depends upon the state of maturation of the cell in the osteoblast lineage. Examinations of numerous cell lines and primary cell cultures from the multipotent fetal rat calvarial cells to the osteocyte cell line MLO-Y4 have occurred. These experiments indicate that as cells become more mature, the stimulatory effect of the microrough surface on differentiation becomes attenuated. It is, however, only on textured surfaces and only in the presence of bone morphogenic protein-2 (BMP-2), that fetal rat calvarial cells are able to establish three dimensional nodules that form mineral in a physiological relevant manner. The results support in vivo observations that a mineral can affect cells directly on the surface as well as distal to the biomaterial indicating that the extracellular signaling factors released by the cells in direct contact with material are sensed by other cells in the microenvironment, and potentially systematically as well.

The surface texture is created by the distribution of pores which do not continue throughout the hydrogel, or stated differently, are superficially located on the hydrogel substrate. These pores can be broken into at least two size groups: large pores and small pores. The large pores can range in size from 3 to 1000 micrometers in diameter. Preferably, the large pores can range in size from 10 to 300 micrometers in diameter. And preferably, the large pores can range in size from 30 to 100 micrometers in diameter. The small pores are smaller in diameter. For example, the small pores can range in size from 0.5 to 20 micrometers in diameter. Preferably, the small pores can range in size from 1 to 10 micrometers. And preferably, the small pores can range in size from 2 to 5 micrometers. The present invention also provides for third, fourth, fifth, and greater numbers of pore sizes on the hydrogel substrate.

FIG. 2 depicts a superficial pore 20 as envisioned by the present invention. The superficial pore contains a large pore 10 and a small pore 15. The small pores 15 are located within the large pore 10. The small pores 15, in this embodiment, are equally spaced from one another by one diameter and are positioned in a hexagonal layout.

The pores on the textured surface in this embodiment enable the surface to resemble native bone which has undergone osteoclastic resorption. Increasing the porosity of a PVA-H generally reduces the mechanical strength of the implant. When surface textured hydrogels are used to provide the requisite surface texture, it is advantageous for the pores not to extend throughout the hydrogel, but instead be limited to a relatively shallow depth below the textured surface. The thickness of the porous portion of the hydrogel is less than 1 millimeter, preferably less than 500 micrometers, and preferably less than or equal to about 200 micrometers.

In order to measure differentiation of cells into bone or bone-like cells four markers are known in the art. The presence of alkaline-phosphatase, TGF- β 1, PGE₂, and osteocalcin function as reliable indicators of cellular differentiation into bone or bone-like cells. Specifically, it has been shown that MG63 osteoblasts, NHOst cells, and fetal rat calvarial cells will attach to surfaces and then differentiate into secretory osteoblasts that exhibit increased levels of alkaline phosphatase activity and osteocalcin. As surface microroughness increases, levels of PGE₂ in the conditioned medium also increase. PGE₂ stimulates osteoclastic activity at high levels, but is required to be present at low levels for osteoblastic activity to occur. It has been previously shown that the elevated prostaglandin levels that are seen in cultures grown on rough microtopographies appear to be required for enhanced osteogenesis since inhibition of prostaglandin production by indomethacin blocks the increase in osteoblast phenotypic expression on these substrates.

TGF- β 1 levels are also surface dependent. The amount of TGF- β 1 produced by osteoblasts cultured on surfaces is modulated in a surface dependent manner by factors that regulate osteogenesis and subsequent bone resorption. Regulation of TGF- β 1 is important to bone formation for a number of reasons. This growth factor stimulates proliferation of mesenchymal cells and enhances the production of extracellular matrix, particularly of type 1 collagen.

Osteocalcin is the most abundant non-collagenous protein in bone, comprising almost 2% of total protein in the human body. It is important in bone metabolism and is used as a clinical marker for bone turnover, but its precise function remains elusive. With no known enzyme activity, osteocalcin's function depends on its structure. That structure reveals a negatively charged protein surface that places five calcium ions in positions complementary to those in hydroxyapatite, the structural mineral component of bone. In addition to binding to hydroxyapatite, osteocalcin functions in cell signaling and the recruitment of osteoclasts and osteoblasts, which have active roles in bone resorption and deposition, respectively.

The hydrogels of the present invention may contain bioactive factors to further stimulate cell growth or differentiation. These factors, for instance attachment peptides, such as RGD containing peptides, and growth factors such as bone morphogenic proteins, insulin-like growth factor, platelet derived growth factor, fibroblast growth factor, cartilage-derived growth factor, transforming growth factor-beta, and parathyroid hormone related peptide, as well as other regulatory chemicals such as statins, prostaglandins, and mineral ions are well known in the art. These factors may be included in the

hydrogels of this invention singly or in combination, and they may be included with or without their respective binding proteins.

The hydrogels of the present invention may also contain bone or cartilage forming cells (osteoblasts or chondrocytes) or precursor cells to bone and cartilage forming cells such as mesenchymal stem cells or osteoprogenitor cells. These precursor cells have the capacity to differentiate into bone and/or cartilage forming cells. Cells may be included in the hydrogels of the present invention alone or in combination with bioactive factors to further stimulate cell growth or differentiation.

Natural intervertebral discs have a tough outer fibrocartilaginous ring called the annulus fibrosus and a soft, inner, highly elastic structure called the nucleus pulposus. The artificial discs of the present invention may contain an inner core constructed to mimic the physical and mechanical properties of the natural nucleus pulposus, surrounded by an annular region constructed to mimic the physical and mechanical properties of the natural annulus fibrosus.

In one embodiment, these regions comprise hydrogels whose water content, degree of polymerization, and degree of crosslinking are routinely adjusted to produce the requisite physical and mechanical properties. The hydrogel comprising the inner core has a higher water content and/or a lower degree of polymerization and/or a lower degree of crosslinking to produce a relatively soft and elastic hydrogel. The hydrogel comprising the outer annular region has a lower water content and/or a higher degree of polymerization and/or crosslinking to produce a relatively hard outer hydrogel which mechanically is tough and stiff. The hydrogels comprising the upper and lower surfaces may substantially resemble the hydrogel comprising the annular region in terms of physical and mechanical properties, water content, and degrees of crosslinking and polymerization. The additional requirement, however, for the surfaces to be textured may allow or require a different combination of physical and mechanical properties in these hydrogels compared to the hydrogel comprising the outer annular region.

In yet another embodiment of the present invention, the hydrogel substrate can be a load bearing patch which can be used in the repair of partially or predominately damaged tissue. For example, the hydrogel substrate bearing the textured surface of the present invention can be relatively thin and small in diameter. That hydrogel substrate can then be placed where deteriorated, either acutely or chronically, cartilage was removed.

In yet another embodiment of the present invention, the hydrogel substrate can be assembled outside the body in a malleable form. The malleable form of the hydrogel substrate can then be placed in the intended area, be it a spinal disc replacement, knee cartilage replacement, shoulder bursa repair, or other use one skilled in the art would foresee. Once in the proper position, the malleable hydrogel substrate could be hardened or polymerized via photopolymerization. Radiation curing or photopolymerization (photo-induced free radical polymerization) has become an important and useful technique for applying and curing coatings, inks and adhesives. Radiation-curable compositions typically comprise as essential components one or more radiation-curable monomers and a photoinitiator. The compositions are applied as a coating to various articles and surfaces and the monomers are polymerized to form a film by exposing the coating of the radiation-curable composition to radiation, typically ultraviolet (UV) or electron-beam radiation. Examples of chemical crosslinker groups are vinyl groups, allyl groups, cinnamates, acrylates, diacrylates, oligoacrylates, methacrylates,

dimethacrylates, oligomethacrylates, or other biologically acceptable photopolymerizable groups.

In yet another embodiment of the present invention, the biocompatible material used in implantation is selected from the group of polymers, ceramics, metallics, organo-metallics, or other known biocompatible materials. To be used as described herein, the materials need to be castable, formed by the use of molds, in order to have rendered upon the surfaces of the materials the necessary forms embodied in this invention. Castable ceramics would be a preferred selection as the materials are often formed in manners which resembled native bone or bone structures. Likewise, biocompatible metallic components could be fashioned using the various embodiments of this invention such to direct cellular attachment and proliferation at the surface of the implant.

EXAMPLES

Example 1

A simple mold surface pattern in accordance with this invention, for example, is an array of cylinders which are 5 μm in diameter and 5 μm in height. To construct a mold surface with this pattern, a 4-inch diameter silicon wafer is coated with a 5 μm thick layer of SU-8 2005 by spin coating at 3000 rpm for about 30 seconds. The wafer is then placed on a hotplate at 65° C. for about 1 minute and then at 95° C. for about 2 minutes. The wafer is then exposed to UV light through a photomask defining the array of cylinders using, for example, a mask aligner (Karl Suss MA-6). The exposure time is calculated to give an exposure energy of 75 mJ/cm² at a wavelength of 365 nm. The exposed areas of the photoresist are then crosslinked by heating the wafer on a hotplate at 65° C. for about 1 minute and then at 95° C. for about 1 minute. The unexposed areas of the photoresist are then dissolved away by immersing the wafer in solvent (SU-8 Developer, MicroChem, Newton, Mass.) for about 1 minute with continuous gentle agitation. The completed wafer is then rinsed, for example, with isopropyl alcohol and dried in a stream of nitrogen. Profilometry measurements and evaluation by scanning electron microscopy can be used to verify that the desired surface pattern is produced.

Example 2

A more complicated pattern for a hydrogel mold surface, in accordance with the present invention when generated could for example, consist of an array of cylinders 100 μm in diameter and 100 μm in height. Each cylinder is topped with a smaller array of cylinders, 5 μm in diameter, and 5 μm in height. The construction of such a mold requires two layers of photoresist and two separate exposures of those layers. First, a 4-inch diameter silicon wafer is coated with a 100 μm thick layer of SU-8 2050 by spin coating at 1700 rpm for about 30 seconds. The wafer is then placed on a hotplate at 65° C. for about 4 minutes and then at 95° C. for about 1 minute. The wafer is then exposed to UV light through the photomask defining the array of large cylinders, using, for example, a mask aligner (Karl Suss MA-6). The exposure time is calculated to give an exposure energy of 450 mJ/cm² at a wavelength of 365 nm.

The exposed areas of the photoresist are then cross-linked by heating the wafer on a hotplate at 65° C. for about 1 minute and then at 95° C. for about 9 minutes. Without developing the first layer, the wafer was coated with a 5 μm thick layer of SU-8 2005 by spin coating at 3000 rpm for about 30 seconds. The wafer is then placed on a hotplate at 65° C. for about 1

13

minute and then at 95° C. for about 2 minutes. The wafer is then exposed to UV light through the photomask defining the array of small cylinders using, for example, a mask aligner (Karl Suss, MA-6). The exposure time is calculated to give an exposure energy of 75 mJ/cm² at a wavelength of 365 nm. The exposed areas of the photoresist are then crosslinked by heating the wafer on a hotplate at 65° C. for about 1 minute and then at 95° C. for about 1 minute. Finally, the unexposed areas of both photoresist layers are then dissolved away by immersing the wafer in solvent (SU-8 Developer, MicroChem, Newton, Mass.) for about 9 minutes with continuous gentle agitation. The completed wafer is then rinsed with, for example, isopropyl alcohol and dried in a stream of nitrogen. Profilometry measurements and evaluation by scanning electron microscopy can be used to verify that the desired surface pattern has been produced.

Example 3

Under the methods of this invention, enhanced differentiation of cells into bone or bone-like cells is seen. Specifically, experiments were run using the PVA-H of this invention in multiple forms. This description references FIGS. 3-5 for clarity. As shown in FIG. 3 there were seven conformations of the surface topography taught by this invention used in this experiment—one being smooth hydrogel. Specifically, conformation is described using a two number nomenclature system such as PVA-H 10/2. PVA-H 10/2 refers first to the size of the large pore on the surface. As described above, the large pore can exist in a complex structure resembling a snowflake. The number 10 in the first position represents a large pore of 100 μm in diameter. The number in the second position of the nomenclature system refers to the size and arrangement of the small pores superimposed on the large pore surface. The second position numbers of 2, 5, and 10 refer to a diameter of 2 μm, 5 μm, and 10 μm, respectively. The spacing and orientation of the small pores on the large pore surface follows a hexagonal grid with a spacing between the small pores of twice the diameter of the small pores.

Moving clockwise through FIG. 3, surfaces are shown possessing a 100 μm large pore with a 2 μm small pore (10/2) **50**, a 100 μm large pore with a 5 μm small pore (10/5) **55**, a 100 μm large pore with a 10 μm small pore (10/10) **60**, no large pore with 10 μm small pores (0/10) **65**, no large pore with 5 μm small pores (0/5) **70**, and no large pore with 2 μm small pores (0/2) **75**. Not shown is smooth PVA-H which would receive the 0/0 designation in the above described nomenclature.

FIGS. 4 and 5 when taken together indicate that while tissue culture plastic provides for the greatest amount of cellular proliferation, textured PVA-Hs promote increased differentiation into bone or bone-like cells. MG63 cells were cultured in conditioned media on the surfaces. Specifically, the cells cultured on the 10/10 conformation **60** showed the greatest level of secreted osteocalcin. The next highest amount of osteocalcin secretion was seen in the 10/5 conformation **55**. This indicates the enhanced ability to generate differentiation into bone or bone-like cells by the mimicking of native osteoclastic resorption sites on PVA-H by the use of the present invention.

FIG. 6 is an image of the surface of a substrate manufactured in accordance with the present invention. The image shows the surface of a hydrogel that was cast in a mold similar to those depicted in FIG. 3. It should be noted that the sub-

14

strate could have been generated with this pattern out of any of the materials described herein.

Example 4

Solid polystyrene objects having complex shapes may be fabricated from uniform polystyrene beads by chemically attaching beads of different sizes. This is illustrated by the following example.

To a suspension of carboxyl-modified polystyrene beads (20.3 μm+/-0.43 μm diameter, Bangs Laboratories) in 20 mM MES, pH 4.5 is added a 10-fold excess of water-soluble carbodiimide, 1-Ethyl-3-(3-dimethylaminopropyl)carbodiimide hydrochloride. After 15 minutes at room temperature, the beads are washed twice by centrifugation and suspension in 20 mM HEPES, pH 7.5 and then resuspended in the same buffer. This suspension is added to a stirred suspension of a sufficient amount of amino-modified polystyrene beads (3.10 μm+/-0.06 μm diameter, Bangs Laboratories) to give a 25-fold molar excess of amino groups over carboxyl groups, in the same buffer. After 3 hours at room temperature, the unreacted excess smaller beads are removed. Microscopic examination shows substantially monodisperse particles composed of 20-μm beads having the majority of their surface covered with a single layer of 3-μm beads.

The polystyrene objects of the foregoing example may be used as a template to fabricate a mold for providing the desired porous surface of the hydrogels of the present invention. This may be accomplished by making a metallic replica of a surface comprising a plurality of polystyrene objects using sputtering and/or metal plating techniques and the like, all of which are well known to those skilled in the art. The metallic replica thus produced may be replicated again and reinforced with further metal or other components, again using methods well known to those skilled in the art. The result is a mold suitable for producing the complex surface texture of the hydrogels of the present invention.

Although the invention has been described with reference to a particular preferred embodiment with its constituent parts, features and the like, these are not intended to exhaust all possible arrangements, mechanical and electrical equivalents, or features, and indeed many other modifications and variations will be ascertainable to those of skill in the art.

What is claimed is:

1. An implant configured for insertion into a patient's joint, said implant comprising:

a first surface and a depth extending from the first surface to a second surface generally opposite the first surface; a plurality of first cavities along the first surface of the implant, each of said first cavities extending to a bottom surface of said first cavity;

wherein the first cavities are larger than the second cavities; and

a plurality of second cavities located below at least one of the first cavities, each of said second cavities extending from the bottom surface of at least one of the first cavities;

wherein said first cavities are only located on the first surface of the implant and do not extend throughout the depth of said implant; and

wherein the second cavities do not extend throughout the depth of the implant.

2. The implant of claim 1, wherein the implant is a load bearing device that is configured for implantation in a knee, shoulder or spine.

15

3. The implant of claim 1, wherein the first cavities promote differentiation of a first cell type, and wherein the second cavities promote differentiation of a second cell type.

4. The implant of claim 1, wherein at least some of the first cavities promote attraction of bone cells.

5. The implant of claim 1, wherein at least some of the second cavities promote anchoring and growth of bone cells.

6. The implant of claim 1, wherein the implant comprises bone and cartilage forming cells or precursor cells to bone and cartilage forming cells.

7. The implant of claim 1, wherein the implant comprises one or more of the following cells types: osteoblasts, chondrocytes, mesenchymal stem cells and osteoprogenitor cells.

8. The implant of claim 1, wherein said implant comprises at least one bioactive factor to stimulate growth or differentiation of cells.

9. The implant of claim 1, wherein the first cavities and the second cavities are within 1 millimeter of the first surface of the implant.

10. The implant of claim 1, wherein the first cavities and the second cavities are within 200 micrometers of the first surface of the implant.

11. The implant of claim 1, wherein the implant comprises a moisture content of at least 5% w/w of the overall of the implant.

12. The implant of claim 1, wherein the implant comprises a moisture content of at least 30% w/w of the overall of the implant.

13. The implant of claim 1, wherein the first cavities have an average cross-section of between 10 to 300 micrometers.

14. The implant of claim 1, wherein the first cavities have an average cross-section of between 30 and 100 micrometers.

16

15. The implant of claim 1, wherein the second cavities have an average cross-section of between 1 to 10 micrometers.

16. The implant of claim 1, wherein the second cavities have an average cross-section of between 2 to 5 micrometers.

17. The implant of claim 1, wherein the implant comprises a hydrogel.

18. A biocompatible substrate having an outer surface and a depth, the biocompatible substrate comprising:

10 a plurality of first cavities along the outer surface of the biocompatible substrate, each of said first cavities extending to a bottom surface of said first cavity; and

a plurality of second cavities located below at least one of the first cavities, each of said second cavities extending from the bottom surface of the first cavity;

wherein the first cavities are larger than the second cavities;

wherein said first cavities are only located along the outer surface of the biocompatible substrate and do not extend throughout the depth of said biocompatible substrate;

wherein said second cavities do not extend throughout the depth of the biocompatible substrate; and

wherein the biocompatible substrate is a load bearing device that is configured for implantation in a joint.

19. The biocompatible substrate of claim 18, wherein the first cavities and the second cavities are within 1 millimeter of the outer surface of the biocompatible substrate.

20. The biocompatible substrate of claim 18, wherein the first cavities have an average cross-section of between 10 to 300 micrometers.

* * * * *